


DAMASK EWALL MOKA GOLD DAMASK *Ceramic*



PART NUMBER
PO1852-INDM00

VARIATION
MEDIUM

THICKNESS
5/16"

NOTES

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

PROFILE
TILE

GROUT JOINT
1/16"

AVAILABILITY
AVAILABLE ON REQUEST

DIMENSIONS
1pc=40cm X 80cm=3.44sqft

APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR FREEZE/THAW	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	No	Wall Only	No	Yes	Yes	No	Yes	Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Bond Strength - EN 12004	Class C2	Bond Strength - EN 1348	³ 1.0 N/mm ²
Breaking Strength - ISO 10545-4	S ³ 600 N	Coefficient of Thermal Linear Expansion - ISO 10545-8	²⁷ MK-1
Crazing Resistance - ISO 10545-11	Resistant	Bending Resistance - ISO 10545-4	R ³ 15 N/mm ²
Moisture Expansion - ISO 10545-10	² 0.06% (0.6mm/m)	Reaction to Fire - N/A	A1
Regularity of Length & Width - ISO 10545-2	± 0.2% ± 0.8 mm	Regularity of Rectangularity - ISO 10545-2	± 0.2% ± 0.8 mm
Regularity of Straightness of Sides - ISO 10545-2	± 0.2% ± 0.8 mm	Release of Dangerous Substances: ISO 10545-15	³ 0.01 mg/dm ² Cd, ³ 0.1 mg/dm ² Pb
Resistance to Household Chemicals - ISO 10545-13	GA	Resistance to Swimming Pool Salts - ISO 10545-13	GA
Surface Flatness - ISO 10545-2	± 0.3% ± 1.3 mm	Water Absorption - ISO 10545-3	10% < EB ² 20 %