

## 16" X 32" EWALL ORANGE Ceramic



PART NUMBER  
PO1854-163200

PROFILE  
TILE

AVAILABILITY  
SPECIAL ORDER

GROUT JOINT  
1/16"

DIMENSIONS  
1pc=40cm x 80cm =3.44sqft

THICKNESS  
5/16"

### NOTES

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

### APPLICATION AREA

WALL	FLOOR	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND	INTERIOR
Yes	No	No	Yes	Yes	No	Yes	Yes	Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

### TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Bond Strength - EN 12004	Class C2	Bond Strength - EN 1348	<sup>3</sup> 1.0 N/mm <sup>2</sup>
Breaking Strength - ISO 10545-4	S <sup>3</sup> 600 N	Coefficient of Thermal Linear Expansion - ISO 10545-8	<sup>27</sup> MK:1
Crazing Resistance - ISO 10545-11	Resistant	Bending Resistance - ISO 10545-4	R <sup>3</sup> 15 N/mm <sup>2</sup>
Moisture Expansion - ISO 10545-10	<sup>2</sup> 0.06% (0.6mm/m)	Reaction to Fire - N/A	A1
Regularity of Length & Width - ISO 10545-2	± 0.2% ± 0.8 mm	Regularity of Rectangularity - ISO 10545-2	± 0.2% ± 0.8 mm
Regularity of Straightness of Sides - ISO 10545-2	± 0.2% ± 0.8 mm	Release of Dangerous Substances: ISO 10545-15	<sup>3</sup> 0,01 mg/dm <sup>2</sup> Cd, <sup>3</sup> 0,1 mg/dm <sup>2</sup> Pb
Resistance to Household Chemicals - ISO 10545-13	GA	Resistance to Swimming Pool Salts - ISO 10545-13	GA
Surface Flatness - ISO 10545-2	± 0.3% ± 1.3 mm	Water Absorption - ISO 10545-3	10% < EB <sup>2</sup> 20 %