

GROOVE 18" X 48" WHITE (G) Ceramic

PART NUMBER PROFILE CR2735-1848G0 TILE

DIMENSIONS THICKNESS ORIGIN

17.57" x 46.97" = 5.731 sqft 7mm Spain

AVAILABILITY

REGULAR STOCK

NOTES

Due to the inherent characteristics of ceramic, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

| WALL | FLOOR | EXTERIOR | STEAM SHOWER | WET R AREA | POOL | BACKSPLASH | FIREPLACE SURROUND | INTERIOR |
|------|-------|----------|-----------------|---------------|------|------------|-----------------------|----------|
| Yes | No | No | Yes | Yes | No | Yes | Yes | Yes |

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

| FEATURES & STANDARD | SPECIFICATION | FEATURES & STANDARD | SPECIFICATION |
|---|---------------|---|---------------|
| Breaking Strength - ISO 10545-4 | S ≥600 N | Coefficient of Thermal Linear Expansion - ISO 10545-8 | ≤7 10-6 / °C |
| Moisture Expansion - ISO 10545-10 | ≤0.2mm/m | Reaction to Fire - N/A | Al |
| Regularity of Length & Width - ISO 10545-2 | Compliant | Regularity of Rectangularity - ISO 10545-2 | Compliant |
| Regularity of Straightness of Sides - ISO 10545-2 | Compliant | Regularity of Thickness - ISO 10545-2 | Compliant |
| Resistance to Household Chemicals - ISO 10545-13 | А | Resistance To Staining - ISO 10545-14 | 5 |
| Resistance to Swimming Pool Salts - ISO 10545-13 | А | Thermal Shock Resistance - ISO 10545-9 | Resistant |
| Water Absorption - ISO 10545-3 | >10% | Water Absorption - ASTM C373-18 | >7% |
| | | | |