

MASON 24" X 24" X 3/4" TAUPE PAVER (T) *Porcelain*



PART NUMBER
PO2468-2424BH

PROFILE
PAVERS

AVAILABILITY
SPECIAL ORDER

GROUT JOINT
1/16"

DIMENSIONS
23.64" x 23.64" = 3.875 sqft

THICKNESS
3/4"

ORIGIN
Italy

NOTES
Available nationwide.

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	Yes	Commercial	Yes	Yes	Yes	Yes	Yes	Yes

INTERIOR

Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Abrasion Resistance - ISO 10545-6	Average Value 140 mm3	Barefoot Ramp Test - DIN 51097	Cl. A+B+C
Breaking Strength - ISO 10545-4	Average Value 14000 N	Frost Resistance - ISO 10545-12	Resistant
Bending Resistance - ISO 10545-4	Average Value 52 N/mm2	Regularity of Length & Width - ISO 10545-2	± 0,15%
Regularity of Rectangularity - ISO 10545-2	± 0,2%	Regularity of Straightness of Sides - ISO 10545-2	± 0,1%
Regularity of Thickness - ISO 10545-2	± 5%	Surface Quality - ISO 10545-2	Compliant
Resistance to Household Chemicals - ISO 10545-13	UA	Resistance To Staining - ISO 10545-14	Cl. 4
Resistance to Swimming Pool Salts - ISO 10545-13	UA	Slip Resistance (Ramp Test) - DIN 51130	R11
Surface Flatness - ISO 10545-2	± 0,35%	Thermal Shock Resistance - ISO 10545-9	Resistant
Water Absorption - ISO 10545-3	Average Value 0,08%		

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION
DCOF - ANSI A.137.1	>0,42 wet

