


RENAISSANCE 2" X 2" NEBBIA BIANCA (P) Porcelain



PART NUMBER PO2322-M002P0

PROFILE MOSAIC DIMENSIONS

IN STOCK THICKNESS

AVAILABILITY

GROUT JOINT 1/16"

ORIGIN

11.81" x 11.81" = .97 sqft 10mm

Italy

NOTES

Available nationwide.

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

WALL	FLOOR		TRAFFIC		EXTERIOR	STEAM SHOWER	WET AREA	POOL
Yes	Residen Use On	tial Floor Y	Reside	ential	Yes	Wall Only	Wall Only	Yes
BACKSPI	LASH	FIREPLACE SURROUND		INTERIOR				
Yes		Yes		Yes				

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION			
Abrasion Resistance - ISO 10545-7	Cl. 4	Breaking Strength - ISO 10545-4	Average Value 3200 N			
Crazing Resistance - ISO 10545-11	Resistant	Frost Resistance - ISO 10545-12	Resistant			
Bending Resistance - ISO 10545-4	Average Value 50 N/mm2	Regularity of Length & Width - ISO 10545-2	± 0,15%			
Regularity of Rectangularity - ISO 10545-2	± 0,2%	Regularity of Straightness of Sides - ISO 10545-2	± 0,1%			
Regularity of Thickness - ISO 10545-2	± 5%	Surface Quality - ISO 10545-2	Compliant			
Resistance To Staining - ISO 10545-14	Cl. 4	Resistance to Swimming Pool Salts - ISO 10545-13	GA			
Surface Flatness - ISO 10545-2	± 0,35%	Thermal Shock Resistance - ISO 10545-9	Resistant			
Water Absorption - ISO 10545-3	Average Value 0,08%	Average Value 0,08% TECHNICAL DATA				
FEATURES & STANDARD	SPECIFICATION	SPECIFICATION				

DCOF - ANSI A. 137. 1

> 0,42 wet