AKDO®

RENAISSANCE MARQUINA BATTISCOPA (P) 2-3/4"X24"   *Porcelain*

PART NUMBER	PROFILE	AVAILABILITY
PO2317-BATTP0	TRIM	AVAILABLE ON REQUEST

GROUT JOINT	DIMENSIONS	THICKNESS
1/16"	2.76'' x 23.62'' = 1.97 lnft	3/8"

ORIGIN

Italy

NOTES

Available nationwide.

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

WALL	FLOOR	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	No	Yes	Wall Only	Wall Only	Yes	Yes	Yes

INTERIOR
Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Abrasion Resistance - ISO 10545-6	Compliant	Breaking Strength - ISO 10545-4	Compliant
Coefficient of Thermal Linear Expansion - ISO 10545-8	^{2} 7 10-6¥C-1	Frost Resistance - ISO 10545-12	Compliant
Coefficient of Restitution - ISO-10545-5	Compliant	Bending Resistance - ISO 10545-4	Compliant
Moisture Expansion - ISO 10545-10	^{2} 0.01% (0.1mm/m)	Reaction to Fire - EN 13501-1	A1fl
Regularity of Length & Width - ISO 10545-2	Compliant	Regularity of Rectangularity - ISO 10545-2	Compliant
Regularity of Straightness of Sides - ISO 10545-2	Compliant	Resistance to Household Chemicals - ISO 10545-13	A
Resistance to Swimming Pool Salts - ISO 10545-13	A	Booted Ramp Test - DIN 51130	R10
Surface Flatness - ISO 10545-2	Compliant	Water Absorption - ISO 10545-3	0.2%

TECHNIC

FEATURES & STANDARD	SPECIFICATION
DCOF - ANSI A.137.1	> 0.42 Wet

LEED

MR
Recycled Content

13,7%

Available self-declared Corporate Sustainability Report (CSR)
conform to Global Reporting Initiative (GRI) Sustainability Report

No VOCs Emission

1,0 - 1,3 W/mK