

18" X 36" TRUST COPPER *Porcelain*



PART NUMBER
PO1690-183600

PROFILE
TILE

AVAILABILITY
AVAILABLE ON REQUEST

GROUT JOINT
1/16"

DIMENSIONS
1pc=45cm X 90cm=4.36sqft

THICKNESS
3/8"

NOTES

Available in northern ca, ct, de, me, ma, nv, nh, nj, ny, pa, ri, vt

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	Yes	Heavy Commercial	Yes	Yes	Yes	Yes	Yes	Yes

INTERIOR

Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD

Abrasion Resistance - ISO 10545-6
 Breaking Strength - ISO 10545-4
 Dynamic Friction Coefficient - METODO B.C.R.A.
 Bending Resistance - ISO 10545-4
 Regularity of Length & Width - ISO 10545-2
 Regularity of Straightness of Sides - ISO 10545-2
 Resistance to Swimming Pool Salts - ISO 10545-13
 Booted Ramp Test - DIN 51130
 Water Absorption - ISO 10545-3

SPECIFICATION

Suitable For
 $S \geq 1300$ N
 > 0.40
 $R \geq 35$ N/mm²
 $\pm 0.1\% \pm 0.1\%$
 $\pm 0.1\%$
 UA
 R10-R12 GRIP
 $\geq 0.5\%$

FEATURES & STANDARD

Barefoot Ramp Test - DIN 51097
 Coefficient of Thermal Linear Expansion - ISO 10545-8
 Frost Resistance - ISO 10545-12
 Scratch Resistance (MOHS) - EN 101
 Regularity of Rectangularity - ISO 10545-2
 Resistance to Household Chemicals - ISO 10545-13
 SCOF - ASTM C1028-96
 Surface Flatness - ISO 10545-2

SPECIFICATION

A+B+A+B+C GRIP
 ≥ 9 MK-1
 Resistant
 8
 $\pm 0.1\%$
 UA
 ≥ 0.60 DRY ≥ 0.60 WET
 Not applicable

TECHNICAL DATA

FEATURES & STANDARD

DCOF - ANSI A.137.1

SPECIFICATION

$> .42$ (actual score .60)

LEED

MR

Recycled Content

40% pre-consumer
 recycled material
 akdo.com