

## 24" X 24" TRUST SILVER *Porcelain*



PART NUMBER  
PO1694-242400

PROFILE  
TILE

AVAILABILITY  
AVAILABLE ON REQUEST

GROUT JOINT  
1/16"

DIMENSIONS  
1pc=60cm X 60cm=3.875sqft

THICKNESS  
3/8"

### NOTES

Available in northern ca, ct, de, me, ma, nv, nh, nj, ny, pa, ri, vt

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

### APPLICATION AREA

| WALL | FLOOR | TRAFFIC             | EXTERIOR | STEAM<br>SHOWER | WET<br>AREA | POOL | BACKSPLASH | FIREPLACE<br>SURROUND |
|------|-------|---------------------|----------|-----------------|-------------|------|------------|-----------------------|
| Yes  | Yes   | Heavy<br>Commercial | Yes      | Yes             | Yes         | Yes  | Yes        | Yes                   |

### INTERIOR

Yes

### TECHNICAL DATA

| FEATURES & STANDARD                               | SPECIFICATION            | FEATURES & STANDARD                                   | SPECIFICATION         |
|---|--------------------------|---|-----------------------|
| Abrasion Resistance - ISO 10545-6                 | Suitable For             | Barefoot Ramp Test - DIN 51097                        | A+B+A+B+C GRIP        |
| Breaking Strength - ISO 10545-4                   | S ≥ 1300 N               | Coefficient of Thermal Linear Expansion - ISO 10545-8 | ± 9 MK-1              |
| Dynamic Friction Coefficient - METODO B.C.R.A.    | > 0.40                   | Frost Resistance - ISO 10545-12                       | Resistant             |
| Bending Resistance - ISO 10545-4                  | R ≥ 35 N/mm <sup>2</sup> | Scratch Resistance (MOHS) - EN 101                    | 8                     |
| Regularity of Length & Width - ISO 10545-2        | ± 0.1% ± 0.1%            | Regularity of Rectangularity - ISO 10545-2            | ± 0.1%                |
| Regularity of Straightness of Sides - ISO 10545-2 | ± 0.1%                   | Resistance to Household Chemicals - ISO 10545-13      | UA                    |
| Resistance to Swimming Pool Salts - ISO 10545-13  | UA                       | SCOF - ASTM C1028-96                                  | ≥ 0.60 DRY ≥ 0.60 WET |
| Booted Ramp Test - DIN 51130                      | R10-R12 GRIP             | Surface Flatness - ISO 10545-2                        | Not applicable        |
| Water Absorption - ISO 10545-3                    | ≤ 0.5%                   |   |                       |

### TECHNICAL DATA

#### FEATURES & STANDARD

DCOF - ANSI A.137.1

#### SPECIFICATION

>.42 (actual score .60)

### LEED

#### MR

Recycled Content

40% pre-consumer  
recycled content