# AKDO

#### 24'' X 24'' TRUST SILVER Porcelain



PART NUMBER	PROFILE	AVAILABILITY	
PO1694-242400	TILE	AVAILABLE ON REQUEST	
GROUT JOINT	DIMENSIONS	THICKNESS	
1/16"	1pc=60cm X 60cm=3.875sqft	3/8"	
NOTES Available in northern ca, ct, de, me, ma, nv, nh, nj, ny, pa	, ri, vt		

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

#### APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	Yes	Heavy Commercial	Yes	Yes	Yes	Yes	Yes	Yes

#### INTERIOR

#### Yes

#### TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Abrasion Resistance - ISO 10545-6	Suitable For	Barefoot Ramp Test - DIN 51097	A+B=A+B+C GRIP
Breaking Strength - ISO 10545-4	S <sup>3</sup> 1300 N	Coefficient of Thermal Linear Expansion - ISO 10545-8	<sup>2</sup> 9 MK-1
Dynamic Friction Coefficient - METODO B.C.R.A.	> 0.40	Frost Resistance - ISO 10545-12	Resistant
Bending Resistance - ISO 10545-4	R <sup>3</sup> 35 N/mm2	Scratch Resistance (MOHS) - EN 101	8
Regularity of Length & Width - ISO 10545-2	± 0.1%=± 0.1%	Regularity of Rectangularity - ISO 10545-2	± 0.1%
Regularity of Straightness of Sides - ISO 10545-2	± 0.1%	Resistance to Household Chemicals - ISO 10545-13	UA
Resistance to Swimming Pool Salts - ISO 10545-13	UA	SCOF - ASTM C1028-96	<sup>3</sup> 0.60 DRY <sub>3</sub> 0.60 WET
Booted Ramp Test - DIN 51130	R100R12 GRIP	Surface Flatness - ISO 10545-2	Not applicable
Water Absorption - ISO 10545-3	<sup>2</sup> 0.5%	TECHNICAL DATA	

#### FEATURES & STANDARD

SPECIFICATION

DCOF - ANSI A.137.1

### >.42 (actual score .60)

#### LEED

## MR

Recycled Content

40% pre-consumer recycled content