

## 6" X 6" TRUST SILVER NON RECTIFIED *Porcelain*



PART NUMBER  
PO1694-060600

VARIATION  
MEDIUM

THICKNESS  
3/8"

### NOTES

Available in northern ca, ct, de, me, ma, nv, nh, nj, ny, pa, ri, vt

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

PROFILE  
TILE

GROUT JOINT  
1/16"

AVAILABILITY  
AVAILABLE ON REQUEST

DIMENSIONS  
1pc=1.5cm X 1.5cm=0.24sqft

### APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR FREEZE/THAW	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	Yes	Heavy Commercial	Yes	Yes	Yes	Yes	Yes	Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

### TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Abrasion Resistance - ISO 10545-6	Suitable For	Barefoot Ramp Test - DIN 51097	A+B:A+B+C GRIP
Breaking Strength - ISO 10545-4	S <sup>3</sup> 1300 N	Coefficient of Thermal Linear Expansion - ISO 10545-8	<sup>2</sup> 9 MK-1
Dynamic Friction Coefficient - METODO B.C.R.A.	> 0.40	DCOF - ANSI A.137.1	>.42 (actual score .60)
Frost Resistance - ISO 10545-12	Resistant	Bending Resistance - ISO 10545-4	R <sup>3</sup> 35 N/mm2
Scratch Resistance (MOHS) - EN 101	8	Regularity of Length & Width - ISO 10545-2	± 0.1%±± 0.1%
Regularity of Rectangularity - ISO 10545-2	± 0.1%	Regularity of Straightness of Sides - ISO 10545-2	± 0.1%
Resistance to Household Chemicals - ISO 10545-13	UA	Resistance to Swimming Pool Salts - ISO 10545-13	UA
SCOF - ASTM C1028-96	<sup>3</sup> 0.60 DRY- <sup>3</sup> 0.60 WET	Booted Ramp Test - DIN 51130	R10-R12 GRIP
Surface Flatness - ISO 10545-2	Not applicable	Water Absorption - ISO 10545-3	<sup>2</sup> 0.5%