## AKDO

### TRUST 24'' X 24'' X 3/4'' SILVER PAVER (T) Porcelain



# PART NUMBER PROFILE PO1694-2424SP PAVERS GROUT JOINT DIMENSIONS

1pc=60cm X 60cm=3.875sqft

AVAILABILITY SPECIAL ORDER THICKNESS

3/4"

NOTES

1/16"

Available in northern ca, ct, de, me, ma, nv, nh, nj, ny, pa, ri, vt

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

#### APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	Yes	Commercial	Yes	Yes	Yes	Yes	Yes	Yes

#### INTERIOR

#### Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

#### TECHNICAL DATA

ATION FEATURES & STANDARD	Specification
Barefoot Ramp Test - DIN 51097	A+B+C
Bond Strength - EN 1348	≥1.0 N/mm2
N Coefficient of Thermal Linear Expansion - ISO	10545-8 ≤7MK-1
>0.40Bagnato Dynamic Friction Coefficient - METODO B.C.I	R.A. > 0.40
Impact Resistance - ISO 10545-5	≥0.55
nm2 Scratch Resistance (MOHS) - EN 101	8
.1mm/m) Reaction to Fire - N/A	Al - Alfi
Regularity of Rectangularity - ISO 10545-2	Compliant
Regularity of Thickness - ISO 10545-2	Compliant
Resistance To Staining - ISO 10545-14	5
SCOF - ASTM C1028-96	<sup>3</sup> 0.60 DRY <sup>_3</sup> 0.60 WET
Surface Flatness - ISO 10545-2	Not Applicable To "Strong" Structures
Water Absorption - ISO 10545-3	≤0.1%
Pendulum Friction Test - AS/NZS 4586	Class P4
Pendulum Friction Test - BS 7976-2002 (CEN/TS 16165	, Annex C) ≥36Dry ≥36Wet
r	Bond Strength - EN 1348 DN Coefficient of Thermal Linear Expansion - ISO Dynamic Friction Coefficient - METODO B.C. Impact Resistance - ISO 10545-5 mm2 Scratch Resistance (MOHS) - EN 101 Reaction to Fire - N/A Regularity of Rectangularity - ISO 10545-2 Regularity of Thickness - ISO 10545-2 Resistance To Staining - ISO 10545-14 SCOF - ASTM C1028-96 Surface Flatness - ISO 10545-3 Pendulum Friction Test - AS/NZS 4586

#### TECHNICAL DATA

FEATURES & STANDARD

DCOF - ANSI A.137.1

> 0.42 Wet

#### LEED

#### MR Recycled Content

20% pre-consumer recycled content