

2 - 7/8" X 36" BATTISCOPA ETIC PALISSANDRO *Porcelain*



PART NUMBER	PROFILE	AVAILABILITY
PO1752-BATT00	TRIM	SPECIAL ORDER
GROUT JOINT	DIMENSIONS	THICKNESS
1/16"	1pc=7.2cm X 90cm=2.95lft	3/8"

NOTES

Available in sf bay area, ct, de, me, ma, nh, nj, ny, pa, ri, vt

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

APPLICATION AREA

WALL	FLOOR	EXTERIOR	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND	INTERIOR
Yes	No	Yes	Yes	Yes	Yes	Yes	Yes	Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Abrasion Resistance - ISO 10545-6	< 150 mm ³	Barefoot Ramp Test - DIN 51097	A
Bond Strength - EN 12004	Class C2	Bond Strength - EN 1348	≥ 1.0 N/mm ²
Breaking Strength - ISO 10545-4	S ≥ 2000 N	Chemical Resistance - ISO 10545-13	Resistant
Coefficient of Thermal Linear Expansion - ISO 10545-8	≈ 7 MK ⁻¹	Coefficient of Friction - B.C.R.A. Rep. CEC/81	>0.40 Asciutto, >0.40 Bagnato
Frost Resistance - ISO 10545-12	Resistant	Impact Resistance - ISO 10545-5	≥ 0.55
Bending Resistance - ISO 10545-4	R ≥ 45 N/mm ²	Scratch Resistance (MOHS) - EN 101	MOHS 6
Moisture Expansion - ISO 10545-10	≈ 0.01% (0.1 mm/m)	Reaction to Fire - N/A	A1 - A1fl
Regularity of Length & Width - ISO 10545-2	± 0.9 (*) ± 0.6 (**) ± 2.0 (***) ± 0.3% ± 1.0mm	Regularity of Rectangularity - ISO 10545-2	± 0.75 (****) ± 0.5 (*****) ± 2.0 (*****) ± 0.3% ± 1.5mm
Regularity of Straightness of Sides - ISO 10545-2	± 0.75 (****) ± 0.5 (*****) ± 1.5 (*****) ± 0.3% ± 0.8mm	Resistance to Household Chemicals - ISO 10545-13	UA
Resistance to Swimming Pool Salts - ISO 10545-13	UA	Booted Ramp Test - DIN 51130	R9
Surface Flatness - ISO 10545-2	± 0.4% ± 1.8mm	Water Absorption - ISO 10545-3	≈ 0.1%
Water Absorption - ASTM C373-18	≈ 0.5%		

TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION
DCOF - ANSI A.137.1	> 0.42 Wet