

## 9" X 36" AXI GOLDEN OAK *Porcelain*



PART NUMBER  
**PO1844-093600**

PROFILE  
**TILE**

AVAILABILITY  
**AVAILABLE ON REQUEST**

VARIATION  
**MEDIUM**

GROUT JOINT  
**1/16"**

DIMENSIONS  
**1pc=22.5cm X 90cm=2.18sqft**

THICKNESS  
**3/8"**

### NOTES

Available in ct, de, me, ma, nh, nj, ny, pa, ri, vt.

Due to the inherent characteristics of porcelain, there may be variations in color, movement and texture from lot to lot.

### APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR FREEZE/THAW	STEAM SHOWER	WET AREA	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	Yes	Standard Commercial	Yes	Yes	Yes	Yes	Yes	Yes

### TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Abrasion Resistance - ISO 10545-6	≥ 150 mm <sup>3</sup>	Barefoot Ramp Test - DIN 51097	A+B
Bond Strength - EN 12004	Class C2	Bond Strength - EN 1348	≥ 1.0 N/mm <sup>2</sup>
Breaking Strength - ISO 10545-4	S ≥ 2000 N	Chemical Resistance - ISO 10545-13	Resistant
Coefficient of Thermal Linear Expansion - ISO 10545-8	± 7 1/mk-1	Coefficient of Friction - B.C.R.A. Rep. CEC/81	>0.40 Asciutto, >0.40 Bagnato
DCOF - ANSI A.137.1	> 0.42 Wet	Frost Resistance - ISO 10545-12	Resistant
Impact Resistance - ISO 10545-5	≥ 0.55	Bending Resistance - ISO 10545-4	R ≥ 45 N/mm <sup>2</sup>
Scratch Resistance (MOHS) - EN 101	6	Moisture Expansion - ISO 10545-10	± 0.01% (0.1mm/m)
Regularity of Length & Width - ISO 10545-2	± 0.3% ± 1.0 mm	Regularity of Rectangularity - ISO 10545-2	± 0.3% ± 1.5 mm
Regularity of Straightness of Sides - ISO 10545-2	± 0.3% ± 0.8 mm	Resistance to Household Chemicals - ISO 10545-13	UA
Resistance to Swimming Pool Salts - ISO 10545-13	UA	Booted Ramp Test - DIN 51130	R10
Surface Flatness - ISO 10545-2	± 0.4% ± 1.8 mm	Water Absorption - ISO 10545-3	≤ 0.1%
Water Absorption - ASTM C373-18	≤ 0.5%		