## **AKDO**°

## STATUARIO BELLO (P) 1 1/4" SLAB Quartz



PART NUMBER PROFILE AVAILABILITY QZ2444-SL54P0 SLAB IN STOCK

DIMENSIONS THICKNESS 126.00" x 64.00" = 56.00 sqft (+/-) 1-1/4"

NOTES

Due to the inherent characteristics of quartz, there may be variations in color, movement and texture from lot to lot.

## APPLICATION AREA

WALL	FLOOR	TRAFFIC	EXTERIOR	STEAM SHOWER	WET	POOL	BACKSPLASH	FIREPLACE SURROUND
Yes	Yes	Standard Commercial	No	Yes	Yes	No	Yes - Heat not to exceed 392° F	Yes - Heat not to exceed 392° F

INTERIOR

Yes

The performance of surface covering products often depends on installation, environmental, and usage factors unique to each project. AKDO is not responsible for any effects that may be caused to products due to installation, wear from use, or exposure to environmental factors including but not limited to: hard water, chemicals, heat, flame, smoke, dirt or other substances. It is your responsibility to assess the project to determine if the product you are selecting is appropriate considering the unique characteristics of your installation, and to apply appropriate, high quality sealers when necessary. Please consult your installer for more information.

## TECHNICAL DATA

FEATURES & STANDARD	SPECIFICATION	FEATURES & STANDARD	SPECIFICATION
Density - ASTM C373	2.38 g/cm3	Bond Strength - ASTM C482	237 psi
Compressive Strength - ASTM C170	Dry: 23,700 psi / Wet: 22,100 psi	Thermal Expansion - ASTM C531	2.61x10-5 in/in F
Coefficient of Friction - ASTM- C-1028	Dry: 0.78 / Wet: 0.61	Flexural Strength - ASTM C880-09	8,700 psi
Weather Resistant - ASTM C217	No Damage	Modulus of Rupture - ASTM C99-09	9,300 psi
Bending Resistance - ASTM C648	480 lbs	Thermal Shock Resistance - ASTM C484	No Damage Passed 25 Cycles
Water Absorption - ASTM C97-09	0.02%	De-icing Resistance - ASTM C672	No Damage
Chemical Reagents Resistance - ASTM D543	No Damage	Izod Impact - ASTM D256	0.363 ft lbs/in
Specific Gravity - ASTM C97-09	148.3lbs/ft3	Wear Resistance - ASTM C501	139 lw
Mold Resistance - ASTM D6329	No microbial growth		